



JK ENDURA / FBL:

- Natural white board coated on both side.
- High bulk and stiffness.
- FDA Reach ROHS certified.
- FSC Mix can be produced.
- Suitable for high speed printing machines with multicolour printing.

APPLICATION :

Packaging of FMCG products such as Cosmetics , Foods, Pharmaceuticals , Liquor cartons etc

AVAILABLE IN : 200-400 GSM

PRODUCT SPECIFICATION

PARAMETER	UNIT	VALUES
GSM Range	gsm	200-400 ± 3%
BULK	cm ³ /g	1.55- 1.65 ± 5%
Plybond GSM ≥ 300	(J/m ²)	≥ 140
Plybond GSM ≤ 295	(J/m ²)	≥ 130
Roughness (PPS)	microns (μ)	2.0 (Max)
IGT Dry pick (MV)	m/s	1.2 (Min)
ISO Brightness TS	(%)	85 ± 1
C.I.E. Whiteness	(%)	97 (Min)
Gloss at 75o (%)	(%)	45 ± 5
Cobb 60 - T/S	g/m ²	30 ± 5
B/S	g/m ²	35 ± 5
Moisture		.
200 - 400 gsm	(%)	6.0 - 8.5
Stiffness	MN (MD)	152 - 944
	MN (CD)	73 - 483