



JK IV BOARD:

- Bluish white tinted board uncoated on both side.
- Good smoothness on top & bottom surface.
- Even shade on both side
- FSC Mix can be produced
- FDA Reach ROHS certified.

Application: Brand Tags , Visiting cards

AVAILABLE IN : 185-400 GSM

PRODUCT SPECIFICATION

PARAMETER	UNIT	VALUES
GSM Range	gsm	185- 400 ± 3%
BULK	cm ³ /g	1.23-1.30 ± 5%
Plybond GSM	(J/m ²)	≥ 150
Bendsten Smoothness TS	(ml/min)	150-300
Bendsten Smoothness BS	(ml/min)	300-600
ISO Brightness TS	(%)	90 ± 1
ISO Brightness BS	(%)	90 ± 1
C.I.E.Whiteness TS	(%)	125 (Min)
C.I.E.Whiteness BS	(%)	125 (Min)
Cobb 60 - T/S	g/m ²	30 ± 5
B/S	g/m ²	35 ± 5
Moisture 185 - 400 gsm	(%)	6.0 - 8.5
Stiffness	MN (MD)	89 - 528
	MN (CD)	45 - 270