



JK INDUCTION WAD:

- Natural white board uncoated on both side.
- Excellent bulk and stiffness.
- FDA Reach ROHS certified.
- FSC Mix can be produced.

Application: Induction Wad

AVAILABLE IN : 250-430 GSM

PRODUCT SPECIFICATION

PARAMETER	UNIT	VALUES
GSM Range	gsm	250- 430 ± 3%
BULK	cm ³ /g	1.72-1.87 ± 5%
Plybond GSM	(J/m ²)	130 (Min)
Bendsten Smoothness TS		
250-300 gsm TS	ml/min	200-400
250-300 gsm BS	ml/min	600-900
301-430 gsm TS	ml/min	400-700
301-430 gsm BS	ml/min	800-1200
ISO Brightness TS	(%)	84 (Min)
ISO Brightness BS	(%)	75 (Min)
C.I.E. Whiteness	(%)	95 (Min)
Cobb 60 - T/S	g/m ²	30 ± 5
B/S	g/m ²	35 ± 5
Moisture 250 - 430 gsm	(%)	6.0 - 7.0
Stiffness	MN (MD)	345 - 1360
	MN (CD)	173 - 680