



JK Lumina

JK LUMINA - JKPM

Features

- . Long lasting shade
- . Superior strength
- . Excellent dimensional stability
- . Excellent Smoothness

End Uses

- . Printing of Books, Maps, Diaries, Notepad, Scribble Pad, School Exercise Book

AVAILABLE IN : 54-120 GSM

TECHNICAL SPECS									
Sl. No.	Particulars	Unit	JK LUMINA						
			Gsm-54	55/66	68/70	78/80	90	100	120
1	Substance	Gsm	± 2.5 %	± 2.5 %	± 2.5 %	± 2.5 %	± 2.5 %	± 2.5 %	± 2.5 %
2	Bulk	CM3/Gm	1.35 ± 0.05	1.35 ± 0.05	1.35 ± 0.05	1.30+/-0.05	1.25+/-0.05	1.25+/-0.05	1.25+/-0.05
3	Breaking Length -MD	Metre	4000 (Min)	4000 (Min)	4000 (Min)	4000 (Min)	4000 (Min)	4000 (Min)	4000 (Min)
4	Breaking Length -CD	Metre	2500 (Min)	2500 (Min)	2500 (Min)	2500 (Min)	2500 (Min)	2500 (Min)	2500 (Min)
5	Sizing (Cobb-60)	Gsm	22 ± 3	22 ± 3	22 ± 3	22 ± 3	22 ± 3	22 ± 3	22 ± 3
6	Roughness Bendsten	MI./Mint.	250 (max)	250(max)	250 (max)	250 (max)	250 (max)	250 (max)	250 (max)
7	Brightness	%ISO	92 Min	92 Min	92 Min	92 Min	92 Min	92 Min	92 Min
8	Opacity	%ISO	85 (min)	85 (min)	88 (min)	88 (min)	89 (min)	89 (min)	89 (min)