



## JK NEO PUREFIL PE (K1P):

- Natural white board , single coated on one side and finally polycoated on bottom side .
- Good smoothness on top surface for better printability.
- FDA Reach ROHS certified.

**Application: Hot & Cold Beverages**

**AVAILABLE IN : 215-415 GSM**

### PRODUCT SPECIFICATION

PARAMETER	UNIT	VALUES
GSM Range	Gsm	215- 415 ± 3%
BULK	cm <sup>3</sup> /g	1.25-1.27 ± 5%
Plybond	(J/m <sup>2</sup> )	150 (Min)
Roughness (PPS)	(ml/min)	3.0 Max
Gloss at 75o	(ml/min)	28 Min
IGT Dry pick (MV)	(ml/min)	1.2 Min
ISO Brightness TS	(%)	85 ± 1
C.I.E. Whiteness TS	(%)	97 ± 1
Cobb 60 - T/S	g/m <sup>2</sup>	30 ± 5
B/S	g/m <sup>2</sup>	35 ± 5
CD Stretch	%	6.0 to 7.0
Edge Wick	Kg/m <sup>2</sup> /hr	1.2 Max
Surface Tension	Dynes/ cm	38 Min
Adhesion Points	1 Poor, 5 Better	3 Min
Moisture 215 - 415 gsm	(%)	6.0 - 7.0