



JK PUREFIL PE (P1P):

- Natural white uncoated board and finally polycoated on bottom side .
- Good smoothness on top surface for better printability.
- FDA Reach ROHS certified.

Application: Hot & Cold Beverages

AVAILABLE IN : 215-415 GSM

PRODUCT SPECIFICATION

| PARAMETER | UNIT | VALUES |
|------------------------|-----------------------|----------------|
| GSM Range | Gsm | 215-415 ± 3% |
| BULK | cm ³ /g | 1.27-1.30 ± 5% |
| Plybond | (J/m ²) | 150 (Min) |
| Bendsten Smoothness TS | (ml/min) | 150-300 |
| Bendsten Smoothness BS | (ml/min) | 300-600 |
| ISO Brightness TS | (%) | 85 ± 1 |
| C.I.E. Whiteness TS | (%) | 97 ± 1 |
| Cobb 60 - T/S | g/m ² | 30 ± 5 |
| B/S | g/m ² | 35 ± 5 |
| CD Stretch | % | 6.0 to 7.0 |
| Edge Wick | Kg/m ² /hr | 1.2 Max |
| Surface Tension | Dynes/ cm | 38 Min |
| Adhesion Points | 1 Poor, 5 Better | 3 Min |
| Moisture 215 - 415 gsm | (%) | 6.0 - 7.0 |