



JK TUFFPAC GC-2

JK TUFFPAC GC-2:

- Natural white board coated on one side.
- High bulk and stiffness.
- FDA Reach ROHS certified.
- FSC Mix can be produced.
- Suitable for high speed printing machines with multicolour printing.

Application: Packaging of Pharmaceuticals , Liquor cartons etc

AVAILABLE IN : 200-400 GSM

PRODUCT SPECIFICATION

PARAMETER	UNIT	VALUES
GSM Range	gsm	200- 400 ± 3%
BULK	cm ³ /g	1.55-1.75 ± 5%
Plybond GSM ≥ 300	(J/m ²)	≥ 140
Plybond GSM ≤ 295	(J/m ²)	≥ 130
Roughness (PPS)	microns (μ)	1.8 (Max)
IGT Dry pick (MV)	m/s	1.2 (Min)
ISO Brightness TS	(%)	86 ± 1
C.I.E. Whiteness		
	(%)	97 (Min)
Gloss at 75o (%)	(%)	45 ± 5
Cobb 60 - T/S	g/m ²	30 ± 5
B/S	g/m ²	35 ± 5
Moisture 200 - 400 gsm	(%)	6.0 - 8.5
Stiffness	MN (MD)	152 - 670