



## MAPLITHO

### JK SHB (JKPM / CPM)

#### Features

- . Long lasting shade
- . Superior strength
- . Excellent dimensional stability
- . Excellent Smoothness

#### End Uses

- . Printing of Books, Calendar, Maps, Diaries, Notepad, Scribble Pad, School Exercise Book

**AVAILABLE IN : 52-120 GSM**

TECHNICAL SPECS								
Sl. No.	Particulars	Unit	JK SHB					
			54/58	60/70	78/80	90	100	120
1	Substance	Gsm	± 2.5 %	± 2.5 %	± 2.5 %	± 2.5 %	± 2.5 %	± 2.5 %
2	Bulk	CM3/Gm	1.40+/-0.05	1.35+/-0.05	1.30+/-0.05	1.25+/-0.05	1.25+/-0.05	1.25+/-0.05
3	Breaking Length -MD	Metre	4000 (Min)	4000 (Min)	4000 (Min)	4000 (Min)	4000 (Min)	4000 (Min)
4	Breaking Length -CD	Metre	2500 (Min)	2500 (Min)	2500 (Min)	2500 (Min)	2500 (Min)	2500 (Min)
5	Sizing (Cobb-60)	Gsm	22+/-2	22+/-2	22+/-2	22+/-2	22+/-2	22+/-2
6	Roughness Bendsten	Ml./Mint.	250 (max)	250 (max)	250 (max)	250 (max)	250 (max)	250 (max)
7	Brightness	%ISO	88 (Min)	88 (Min)	88 (Min)	88 (Min)	88 (Min)	88 (Min)
8	Opacity	%ISO	88 (min)	89 (min)	90 (min)	90 (min)	90 (min)	90 (min)